

"CABLE WITH FIRE-RESISTANT, MOISTURE-RESISTANT COATING"

5 This application is a continuation of PCT/EP98/01443
filed March 12, 1998 which claims the benefit of United States
Provisional Application 60/050,956 filed June 16, 1997, which
in turn is based on Italian Application MI97 A-000559 filed
March 13, 1997, the contents all of which are incorporated
herein by reference.

10 Background of The Invention

Field of the Invention

 The present invention relates to an electrical cable, in
particular for low-tension power transmission or for
telecommunications, this cable comprising a coating which has
15 fire-resistance properties and is capable of keeping
its electrical insulation properties unchanged when said cable
is in the presence of moisture.

Description of Related Art

 Besides retarding the propagation of fire, cable coatings
20 defined as being "fire resistant" should, in the presence of
fire, afford a very low emission of fumes, a
low level of emission of noxious gases, and should be self-
extinguishing. Combustion-resistant cables are assessed for
use in closed environments by means of performance tests
25 against industrial standards which define the limits and
provide the methodology for cable flammability tests.
Examples of these standards are ASTM 2863 and ASTM E622; IEEE-
383, IEEE-1202 (devised by the "Institute of Electrical and
Electronics Engineers", New York, USA) ; UL-1581 and UL-44
30 ("Underwriters Laboratories Inc.", Northbrook, Illinois, USA);
CSA C22.2 0.3

("Canadian Standard Association", Toronto, Canada).

Typical characteristics of moisture-resistant coatings
are a limited absorption of water and the maintenance of
5 constant electrical properties, even in the presence of
moisture; an example of a reference standard

causing the formation of a whitish compound on the surface of the cable coating.

Neither of these documents mentions the problem of
5 maintaining the dielectric insulation properties after
exposure of the cable to a wet environment, nor the problem of
strippability mentioned above.

GB 2,294,801 discloses a cable having an inner sheath
made of polyethylene (PE) or polypropylene (PP) in contact
10 with the conductive wire and an outer sheath made of fire
retardant material, such as "low smoke zero halogen" rubber or
PVC. The PE or PP employed as materials for the inner layer
are intended as waterproof materials. However, no mention is
made about the fire retardant properties of the
15 said inner layer. As a matter of fact, the presence of the
inner layer consisting essentially of a polyolefinic material
would substantially reduce the overall fire
resistance properties of the cable's sheath.

Summary of the Invention

20 The Applicant has observed that the properties of fire
resistance and of insulation resistance in the
presence of moisture are difficult to reconcile in a
single cable coating, since the fire resistance is
increased the larger the amount of inorganic charge
25 present in the coating, whereas the insulation resistance
in the presence of moisture reduces as the inorganic
charge in the coating increases. The Applicant has also
observed that the presence of suitable coupling agents in the
mixture which forms the coating, while improving the
30 insulation resistance of the coating, lowers its capacity

presence of moisture; and the outer layer comprises a base
polymer matrix and an inorganic charge dispersed in this
5 matrix in an amount such as to provide the cable with the
desired fire-resistance properties.

The Applicant has observed that when the coupling
agent present in the inner layer is a polyolefin compound
containing at least one unsaturation and at least one
10 carboxyl group in the polymer chain (identified in the
remainder of the present description by the term
"carboxylated polyolefin"), the resulting cable not only
has the desired insulation-resistance properties in the
presence of moisture but is also readily strippable.

15 The Applicant has also observed that if a polymer
composition for coating cables does not contain such an
additive or other coupling agent known in the art, or at
any rate contains it in amounts lower than the
abovementioned predetermined amount, when said cable is in
20 the presence of moisture this coating is able to absorb a
certain amount of water, thereby increasing the fire
resistance of this cable.

The Applicant has moreover found that with the
abovementioned double-layer structure of the coating, the
25 outer layer being the one which mainly imparts the fire
resistance, it is possible to add to this outer layer an
amount of inorganic charge which is greater than the
amount of the inner layer, without this having a negative
impact on the dielectric properties of the coating,
30 [whichare] which are, in any case, guaranteed by the presence

of the

inner layer; in this way, the fire resistance of the
5 outer layer is increased both owing to the larger amount of
inorganic charge present and owing to the increased
capacity of said inorganic charge to absorb water (that is
to say more inorganic charge capable of absorbing water).
On the other hand, by endowing the inner layer with
10 substantial fire-resistant properties, thus contributing
to the overall fire-resistant properties of the cable, the
applicant has found that it is possible to advantageously
reduce the thickness of the outer layer of the coating,
with respect to the thickness of an outer layer enveloping
15 an inner layer having no fire-resistant properties.

In this respect, the Applicant has also found that an
advantageous embodiment of the present invention is
obtained by suitably selecting the kind of mineral charge
to be added in the two layers, in such a way to further
20 improve the moisture resistance of the cable coating at
high temperatures.

Brief Description of The Drawings

Fig. 1 schematically shows the cross-sectional drawing of
a cable according to the invention, comprising a conductor (1,
25 a layer of inner coating (2) and a layer of outer coating (3).
The conductor may optionally be coated with a strip of polymer
material, typically polyester, in order to facilitate
detachment of the coating.

Detailed Description

30 A first aspect of the present invention thus relates
to an electrical cable which has predetermined fire-
resistance and electric insulation-resistance properties

in the presence of moisture, this cable comprising a metal conductor and at least one polymer coating consisting of a double layer, in which the outer layer of this coating is
5 designed so as mainly to impart to the cable said fire-resistance properties, and the inner layer is designed so as to impart to the cable said insulation-resistance properties in the presence of moisture, while

of coupling agent, in order to improve the compatibility between the inorganic charge and the polymer matrix, thereby improving the mechanical properties of the coating; this coupling agent may be a carboxylated polyolefin of the type contained in the inner layer or, more preferably, a silane-based compound of the type known in the art.

In this respect, the Applicant has found that the amount of coupling agent required to ensure the right degree of compatibility between the polymer matrix and the inorganic charge is considerably less than the amount required to keep the electrical properties substantially unchanged when the coating is in the presence of moisture. Hence, the fact that the outer layer contains reduced amounts of coupling agent (typically from 10% to 70% by weight relative to the weight required to keep the electrical properties constant in the presence of moisture) allows this layer, when the cable is in the presence of moisture, to still absorb a certain amount of water, thereby increasing the fire resistance of the coating; the electrical properties of the coating are, in any case, ensured by the presence of the inner layer.

The additive which is capable of exerting the fire-resistance effect according to the invention is generally
5 an inorganic oxide, preferably in hydrated or hydroxide form. Examples of suitable compounds are aluminum oxide, bismuth oxide, cobalt oxide, iron oxide, magnesium oxide, titanium oxide and zinc oxide, their respective hydrated forms, and mixtures thereof, in any ratio, based on the
10 particular requirements.

Preferably, these inorganic charges are used in hydrated form, magnesium hydroxide being particularly preferred, aluminum oxide trihydrate ($\text{Al}_2\text{O}_3 \cdot 3\text{H}_2\text{O}$), or mixtures thereof being particularly preferred; limited
15 amounts, generally less than 25% by weight, of one or more inorganic oxides chosen from CoO , PbO , TiO_2 , Sb_2O_3 , ZnO and Fe_2O_3 , or mixtures thereof, preferably in hydrated form, may advantageously be added to these compounds or mixtures.

20 According to a particularly preferred embodiment the inner layer comprises as main compound of mineral charge an aluminum oxide, preferably in hydrated form or as hydroxide.

In the present description the term "main compound"
25 of the mineral charge is intended to refer to the mineral charge which contains typically at least the 75%, preferably the 90% of such compound.

anhydride; it is particularly preferred to use maleic anhydride.

5 In general, the ratio between the carboxylic groups and the unsaturations in the final compound may vary depending on various factors, such as, for example, the amount and composition of the unsaturated compounds and of the carboxylated compounds which are reacted, the amount of inorganic charge present in the coating, and the like.

10 Usually, this carboxyl groups/unsaturations ratio may range from 1:10 to 1:100, a ratio of between 1:10 and 1:50 being preferred.

When the carboxylated polyolefin is formed by reaction between polybutadiene with a polymerization number of about

15 100 and maleic anhydride, the amount of maleic anhydride reacted will generally range from 5 to 25% of the weight of polybutadiene, about 10% by weight being preferable.

An example of a commercially available carboxylated polyolefin which is suitable for the purposes of the present

20 invention is Lithene N4 B10 MA (Revertex Ltd.), which is a maleic-treated polybutadiene.

The amount by weight of coupling agent in the inner layer may vary mainly depending on the type of coupling agent used and on the amount of inorganic charge present; the coupling

25 agent will, however, always be added in an amount which affords the desired insulation-resistance, properties in the presence of moisture. The amount of coupling agent in the [outer] inner layer is generally between 1%